

PRODUCT SPECIFICATION SHEET

BELZONA 1341N

FN10030



GENERAL INFORMATION

Product Description:

A drinking water certified two component coating system for improving the efficiency of fluid handling systems and protecting metals from the effects of erosion-corrosion. Also used as a high strength structural adhesive for bonding or for creation of irregular load bearing shims with good electrical insulation characteristics. For use in Original Equipment Manufacture or repair situations.

Application Areas:

When mixed and applied as detailed in the Belzona Instructions for Use (IFU), the system is ideally suited for application to the following:

- Pumps
- Valves
- Tube sheets
- Heat exchangers
- Water tanks
- Water boxes
- Pipes

APPLICATION INFORMATION

Working Life

Will vary according to temperature. At 68°F (20°C) the working life will be 35 minutes.

Limitations of Use

Belzona 1341N should not be used at temperatures below 50°F (10°C). Where material has been stored below this temperature, warm the Base and Solidifier units until they attain a temperature of 68-77°F (20-25°C).

Cure Time

Allow to cure for the times shown in the Belzona IFU before subjecting it to the conditions indicated.

Volume Capacity

212 in³ (3.475 litres)/5kg unit
31.73 in³ (520cm³)/750g unit
42.4 in³ (695 cm³)/kg

Coverage rate

To achieve the correct film thickness of 10 mils (250 microns) per coat, a practical coverage rate of 19.5 sq.ft (1.8 sq.m) per 750g unit should be obtained or 130 sq.ft (12 sq.m) per 5kg.

Base Component

Appearance Thixotropic paste
Color Gray or Blue
Density 1.58-1.63 g/cm³

Solidifier Component

Appearance Clear liquid
Color Clear
Density 1.17-1.19 g/cm³

Mixed Properties

Mixing ratio by weight 2 : 1
Mixing ratio by volume 3 : 2
Density 1.42-1.46 g/cm³

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

PRODUCT SPECIFICATION SHEET

BELZONA 1341N

FN10030



ABRASION

Taber

The Taber abrasion resistance determined in accordance with ASTM D4060 with 1 kg load is typically:

H10 Wheels (Wet)	52 mm ³ loss per 1000 cycles
CS17 Wheels (Dry)	6 mm ³ loss per 1000 cycles

ADHESION

Tensile Shear

When tested in accordance with ASTM D1002, on grit blasted substrate, typical values will be:

	68°F (20°C) cure
Mild steel	2,500 psi (17.2MPa)
Stainless steel	2,780 psi (19.2MPa)
Copper	2,230 psi (15.4MPa)
Aluminum	1,570 psi (10.8MPa)

	212°F (100°C) cure
Mild steel	3,250 psi (22.4Pa)

Pull Off Adhesion

When tested in accordance with ASTM D 4541/ ISO 4624, the pull off strength from grit blasted steel will be typically:

4030 psi (27.8MPa)

CAVITATION RESISTANCE

When tested to a modified version of ASTM G32 using stationary specimens at 20KHz frequency and 50 microns amplitude a typical volume loss will be 12 mm³/hour.

CHEMICAL RESISTANCE

Once fully cured, the material will demonstrate excellent resistance to most commonly found inorganic acids and alkalis at concentrations up to 10%.

The material is also resistant to hydro-carbons, mineral oils, lubricating oils and many other commonly found chemicals.

* For a more detailed description of chemical resistance properties, refer to relevant Chemical Resistance chart.

COMPRESSIVE PROPERTIES

When determined in accordance with ASTM D695, typical values will be:

Compressive yield strength	Cure temperature
6,900 psi (47.6MPa)	68°F (20°C)
8,500 psi (58.6MPa)	212°F (100°C)

CORROSION PROTECTION

Cathodic Disbondment

When tested in accordance with ASTM G8 typical values obtained will be: Class B.

FLEXURAL PROPERTIES

When determined in accordance with ASTM D790, typical values will be:

Flexural Strength	Cure temperature
5,900 psi (40.7MPa)	68°F (20°C)
6,400 psi (44.1MPa)	212°F (100°C)

HARDNESS

Shore D

When determined in accordance with ASTM D2240, typical values will be:

	Cure temperature
73	68°F (20°C)
79	212°F (100°C)

Barcol

When determined in accordance with ASTM D2583, will typically be:

	Cure temperature
63	68°F (20°C)
75	212°F (100°C)

Koenig Pendulum

When tested to ISO 1522 the Koenig damping time will be typically:

	Cure temperature
108 seconds	68°F (20°C)
125 seconds	212°F (100°C)

HEAT RESISTANCE

Heat Distortion Temperature (HDT)

Tested to ASTM D648 (264 psi fiber stress), typical values obtained will be:

	Cure temperature
111°F (44°C)	68°F (20°C)
160°F (71°C)	212°F (100°C)

Heat Resistance

For many typical applications the material is suitable for continuous immersion in aqueous solutions up to 140°F (60°C). The material will be stable under dry conditions up to 392°F (200°C) and down to -40°F (-40°C).

PRODUCT SPECIFICATION SHEET

BELZONA 1341N

FN10030



IMPACT RESISTANCE

Impact Strength

The impact strength (reverse notched) when tested to ASTM D256 is typically:

1 ft.lb./in (54 J/m)
1.15 ft.lb./in (62 J/m)

Cure temperature
68°F (20°C)
212°F (100°C)

POTABLE WATER APPROVAL

Belzona 1341 bearing the NSF mark is listed for contact with drinking water subject to the following restrictions. For use on distribution line pumps of >4 inch diameter with a minimum daily output of 4800 gallons/ft² of coated pump surface For use on tanks of >100,000 gallons.



Certified to
NSF/ANSI 61

PUMP EFFICIENCY ENHANCEMENT

The **Belzona 1341N** system has been shown to be capable of bringing about an increase in pump efficiency of up to 7% in Independent tests carried out by the National Engineering Laboratory, East Kilbride, Glasgow, Scotland, test number 0230 432/88 BEM/01 and the Aurora Pump Company, North Aurora, Illinois, test number 0789089/1089037.

THERMAL EXPANSION

When tested in accordance with ASTM E228 typical values obtained will be:

74.7 ppm/°C

SHELF LIFE

Separate base and solidifier components shall have a shelf life of at least 3 years when stored between 32°F (0°C) and 86°F (30°C).

APPROVALS/ACCEPTANCES

The material has received recognition from organizations worldwide including:

NSF
U.S.D.A.
INGERSOLL RAND
SULZER PUMPS
SPP LTD.
SSW PUMP SERVICES
AURORA PUMPS

PRODUCT SPECIFICATION SHEET

BELZONA 1341N

FN10030



WARRANTY

Belzona guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, ISO etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 1341N is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

MANUFACTURER

Belzona Polymerics Ltd.
Claro Road, Harrogate,
HG1 4DS, UK

Belzona Inc.
2000 N.W. 88th Court,
Miami, Florida, USA, 33172

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2013 Belzona International Limited. Belzona® is a registered trademark.



ISO 9001:2008
Q 09335
ISO 14001:2004
EMS 509612

Manufactured under an ISO 9000
Registered Quality Management System

